

#### Better chemistry. Better business.

Hubbard-Hall Inc. • 563 South Leonard Street, Waterbury, CT 07608 • HubbardHall.com • 800-648-3412

#### **Product Bulletin**

Product Name: Quick Pik 1 Product Code: 2541020 Revision Date: June 24, 2020

# Quick Pik 1

Quick Pik 1 is a combination of dry, free-flowing acids used as a water solution at temperatures ranging from ambient to 180°F. The higher temperatures are generally required where rust is a problem. Quick Pik 1 is a convenient substitute for the more difficult-to-handle liquid acids. At ambient temperatures, venting will not be necessary.

Quick Pik 1 is not as harsh in its action on metal surfaces as are the common mineral acids. It may be used to remove oxides and to activate steel, stainless steel, zinc plate and zinc die castings as well as copper and its alloys. It is used prior to all types of finishing operations.

### **Features & Benefits**

Dry acid salt	No fumes; safer work
	environment
No chlorides	Effective SS activator, non- pitting; less rejects
	Longer equipment life

# **Typical Applications**

- · Used in any plating, job or captive shop
- Used online in any shop where metal is used

Quick Pik 1 solutions must be contained in acid-resistant tanks and containers. Polypropylene, Polyethylene, PVC or lined steel are suitable.

## **Operating Conditions**

Solution makeup

Steel activation	4 – 8 oz/Gal
	30 – 60 sec immersion
Rust removal	16 – 32 oz/Gal
	2 – 5 min immersion
Stainless steel activation	1 – 2 lb/Gal
	2 – 5 min immersion
	150°F – 180°F









#### Better chemistry. Better business.

Hubbard-Hall Inc. • 563 South Leonard Street, Waterbury, CT 07608 • HubbardHall.com • 800-648-3412

**Product Bulletin** 

Product Name: Quick Pik 1 Product Code: 2541020 Revision Date: June 24, 2020

Copper and its alloys	4 – 16 oz/Gal
deoxidizing	30 – 60 sec immersion
Plated and die cast zinc	4 – 8 oz/Gal
deoxidizing	20 – 60 sec

Residual Quick Pik 1 solution must be removed by thorough rinsing prior to further finishing.

### Solution Maintenance

Solution strength is maintained by small periodic additions to maintain the desired activity. It is disposed of only when its effectiveness is diminished by accumulation of metals, dirt, oil, grease, etc. The concentration may be controlled by simple titration method furnished upon request.

### Caution

May cause skin irritation. Do not get in eyes. Avoid prolonged contact with skin. In case of contact with skin or eyes, flush freely with water for at least 15 minutes. For eyes, get medical attention.

WARRANTY: THE QUALITY OF THIS PRODUCT IS GUARANTEED ON SHIPMENT FROM OUR PLANT. IF THE USE RECOMMENDATIONS ARE FOLLOWED, DESIRED RESULTS WILL BE OBTAINED. SINCE THE USE OF OUR PRODUCTS IS BEYOND OUR CONTROL, NO GUARANTEE EXPRESSED OR IMPLIED IS MADE AS TO THE EFFECTS OF SUCH USE, OR THE RESULTS TO BE OBTAINED.

# Our people. Your problem solvers.

For more information on this process please call us at 1-800-648-3412

or techservice@hubbardhall.com











